POROUS POLYMERIC MEMBRANE COMPRISING VINYLIDENE FLUORIDE

The present invention relates to porous polymeric
membranes. The invention relates in particular to a
5 process for producing a porous polymeric membrane and to
the use of such a membrane in a lithium cell or in a fuel
cell.

For many years it has been known to make cells with
10 lithium metal anodes, and cathodes of a material into
which lithium ions can be intercalated or inserted. Such
cells may use, as electrolyte, a solution of a lithium
salt in an organic liquid such as propylene carbonate,
and a separator such as filter paper or polypropylene.
15 More recently the use of a solid-state ion-conducting
polymer has also been suggested as an electrolyte. For
secondary or rechargeable lithium cells, the use of
lithium metal anodes is unsatisfactory as problems arise
from dendrite growth. The elimination of this problem is
20 now possible by employing a material able to intercalate
lithium ions reversibly at very low voltages, such as
graphite, leading to so-called "lithium-ion", " rocking-
chair", or "swing" lithium rechargeable batteries. These
lithium cells operate on the principle that they contain
25 not lithium metal, but lithium ions which are rocked back
and forth between two intercalation materials during the
charging and discharging parts of the cycle.

A polymer electrolyte has been proposed by Gozdz et
30 al.(US 5,296,318), which comprises a copolymer of 75 to
92% vinylidene fluoride and 8 to 25% of
hexafluoropropylene, blended with a lithium salt and a
compatible solvent such as ethylene carbonate/propylene
carbonate mixture and cast from solution in a low
35 boiling-point solvent such as tetrahydrofuran. GB 2 309
701 B (AEA Technology) describes how the adhesion of a

- 2 -

polymeric electrolyte composition can be enhanced by grafting suitable mono-unsaturated groups onto the polymer chain, and in this case the polymeric chain might be a homopolymer PVdF, or a copolymer or terpolymer

5   consisting primarily of vinylidene fluoride. It is also possible to make a solid polymer electrolyte by first making a porous film of the polymer material, and then immersing the film in the solution of lithium salt in an organic solvent so the electrolyte solution combines with

10   the polymer film, as described in EP 0 730 316 A (Elf Atochem). However, with known methods of making porous membranes, it is difficult to achieve micropores of a substantially uniform size and to control the porosity of the resulting film.

15

Fuel cells use a porous membrane to separate the anode and the cathode. The membrane is typically a multilayered assembly and may include, for example, a porous membrane and one or more diffusion layers.

20   Improved membranes are needed to improve the uniform delivery of gas to the fuel cell plate.

The present invention provides a process for producing a porous polymeric membrane which process

25   comprises:

a) preparing a solution comprising a polymer which comprises vinylidene fluoride in a solvent /non-solvent mixture by dispersing the polymer in the non-solvent

30   prior to addition of the solvent wherein the boiling point of the non-solvent is higher than that of the solvent;

b) holding the solution at an elevated temperature

35   of at least 40°C until the polymer is completely solvated;

c) casting the solution to form a thin layer; and

d) drying the thin layer to form a membrane.

The polymer typically comprises primarily vinylidene
fluoride. Thus the polymer may be a homopolymer such as
5 polyvinylidene fluoride (PVdF), or a copolymer of
vinylidene fluoride with, for example hexafluoro-
propylene, or a terpolymer. Typically preferred grades of
polymer are PVdF homopolymer Solvay Solef 1015 or 6020,
copolymers Solvay Solef 20615 or 20815 or Atochem 2801
10 and terpolymers comprising vinylidene fluoride,
hexafluoropropylene and chlorotrifluoroethylene as
described in WO 02/11230.

The polymer may also be a polymer in which the
15 polymeric chain consists primarily of vinylidene
fluoride, onto which is grafted a mono-unsaturated
carboxylic, sulphonic or phosphonic acid, ester, or
amide. The monomer to be grafted onto the polymer chain
should have only one double-bond in the carbon chain R-,
20 and one or more carboxyl groups -COOH, sulphonic acid
groups $-SO_2OH$, phosphonic acid groups $-PO(OH)_2$, ester
groups -COOR', or amide groups $-CONH_2$. Generally smaller
monomers, with less than five carbon atoms in the carbon
chain R-, are preferable. For example acrylic acid;
25 crotonic acid, vinylacetic acid, methylacrylic acid
(which are isomers of butenoic acid); isomers of
pentenoic acid such as allylacetic acid; etc. The
corresponding amides (and substituted amides) may also be
used. In an ester, the group R' might be methyl, ethyl
30 or butyl; for example esters such as methyl acrylate or
butyl acrylate may be used. Some preferred monomers for
grafting are acrylic acid or dimethyl acrylamide, but a
range of other monomers that incorporate the final group
are also suitable.
35

The grafting can be achieved by an irradiation

process. For example the polymer chain substrate and the
graft monomer material together may be subjected to
continuous or intermittent irradiation; or more
preferably the substrate is pre-irradiated before being
5 brought into contact with the monomer material. The
irradiation may be with an electron beam, Gamma-rays or
X-rays. The irradiation activates the substrate (the
polymer chain) apparently by generating free radicals.
The degree of grafting is determined by several factors,
10 the most important being the extent of pre-activation of
the polymer substrate by the irradiation, the length of
time that the activated polymer is in contact with the
graft monomer material, the extent to which the monomer
can penetrate the polymer, and the temperature of the
15 polymer and the monomer when in contact. The degree of
grafting in the resulting material is desirably between 2
and 20% of the final weight, more preferably between 3
and 12%, for example 5% or 10%.

20   Further components may also be present in the
solution for example, viscosity modifiers such as
carboxymethylcellulose and surface tension modifiers such
as oxalic or maleic acid.

25   The polymer is mixed with the non-solvent to form a
slurry and then the solvent is added to form a
homogeneous solution. Typically a slurry of polymer and
non-solvent is formed and heated to about 60°C,
preferably in a non-metallic container (for example of
30 glass, or of a plastic such as polypropylene) with
stirring, and then the solvent is added rapidly (for
example at about 1 litre in 5 seconds).

If the polymer is mixed with the solvent first, and
35 the non-solvent then added to the solution, this
generates a microgel, so the solution is unstable and

- 5 -

does not give reproducible membranes.

The non-solvent is a liquid which does not dissolve
the polymer when used alone. The non-solvent should not
5   only dissolve in the solvent, but it should be miscible
with the solvent in substantially all proportions. The
boiling point of the non-solvent is higher than that of
the solvent, preferably 20°C higher, more preferably 40°C
higher or more. Examples of the non-solvents include
10   alcohols containing 6 to 20 carbon atoms such as,
octanol, decanol and dodecanol, and mixtures thereof,
preferably decanol, dodecanol and mixtures thereof.
Particularly preferred non-solvents are a 50:50 mixture
of dodecanol and decanol or dodecanol alone.

15
The solvent is a liquid which can dissolve or swell
the polymer. The solvent may be chosen from for example
ketones, ethers, N,N-dimethylformamide (DMF), N,N-
dimethylacetamide (DMA), N,N-diethylacetamide, N-methyl-
20   2-pyrrolidone (NMP), hexamethylphosphoramide,
tetramethylurea and dimethyl sulfoxide (DMSO) or a
mixture thereof. DMF and NMP are preferred solvents. More
preferably NMP is the solvent.

25   The ratio of non-solvent to solvent in the solution
can be varied. Typically the proportion of non-solvent in
the solvent/non-solvent mixture is 2 to 30 wt %,
preferably 5 to 15 wt %, more preferably 7 to 10 wt%.

30   The amount of polymer in the solution is generally
from 3 to 30 wt %, preferably from 5 to 20 wt %, more
preferably from 8 to 15 wt %.

Solvation of the polymer takes place at an elevated
35   temperature. An elevated temperature is a temperature
above room temperature (which is taken to be 20°C). The

AMENDED SHEET

- 6 -

temperature chosen is specific to the polymer and
solvent/non-solvent combination that is used and the
amount of time over which solvation takes place. The
elevated temperature is at least 40°C, more typically at
5 least 50°C for example 55°C. A lower temperature may be
used if solvation takes place over a longer period of
time.

Typically solvation takes place over several days.
10 The solvation process continues until the polymer(s) are
completely solvated. The exact solvation time required
varies depending on the solvent/non-solvent mixture, the
choice of polymer or polymers and the temperature used.
Typically solvation takes place over from 4 to 14 days,
15 preferably 5 to 10 days and most preferably 5 to 7 days.
For example, PVdF (Solvay Solef 6020/1001) in N-methyl-2-
pyrrolidone and a 50:50 mixture of decanol and dodecanol
typically solvates completely in from 5 to 14 days,
typically 10 days depending on the ratio of non-solvent
20 to solvent in the solution. Gel formation during the
solvation process is so slow as to be negligible.
Solvation also occurs without the formation of a
microgel.

25 Once the polymer is fully solvated, the solution is
stable at room temperature for several weeks. Thus, the
viscosity of the solution does not change over time, the
colour of the solution remains constant and there is no
separation of the solvent or non-solvent from the
30 solution. Furthermore the solution forms reproducible
membranes with consistent properties, when cast.
Therefore it is not necessary to cast the solution into a
film immediately.

35 The solution is typically cast onto a non-porous
substrate such as aluminium foil or Mylar film. The

aluminium foil is typically about 20 µm thick whereas the
Mylar film is typically about 100 µm thick. The solution
can also be cast onto an anode or cathode if the anode or
cathode is made of a material that is not too porous.

5

When casting the solution, the solution is typically
cast as a thin layer less than 0.5 mm thick, preferably
less than 0.3 mm thick, on the substrate.

10   The film is formed by drying in typically at least
two successive drying zones in a drying machine; the film
is not contacted with any liquids. Preferably the drying
machine has three or four drying zones, most preferably
four drying zones. Different temperatures are maintained
15 in each of the zones and the temperatures increase from
zone to zone in the direction of the film transfer.
Typical temperature values in the drying zones when using
a knife-over-roll continuous method for producing a
membrane on a moving web are as follows:

20

        first zone   from 50°C to 120°C
        second zone   from 80°C to 150°C.

Typical temperature pairings could be, for example, 65°C
25 in the first zone and 100°C in the second zone, or 95°C
in the first zone and 120°C in the second zone. If the
machine has three or four drying zones then the
temperature change from zone to zone can be more gradual.
For example, where the machine has four drying zones, the
30 zones can be set at 65°C, 75°C, 95°C and 110°C in order.

The speed of the moving web typically ranges from
0.2 to 5.0 m/min. The speed of the web varies depending
on the length of the drying zone and the number of zones.
35 The more zones the machine has, the faster the web can be
run without adverse effects on the properties of the

- 8 -

membrane.

The solution is dried to form a membrane in the presence of a gas. In one embodiment the gas is dry gas,
5 for example dry air. For example, air with a dewpoint of less than $-20°C$, for example from $-35°C$ to $-37°C$ may be used. However, the gas need not be anhydrous. The gas may also be humid air, for example air supplied at ambient conditions of 34% relative humidity at 16°C. However if
10 air humidity varies, the membrane's permeability will also vary.

The porosity of the resulting porous polymeric membrane can be controlled by varying the ratio of non-
15 solvent to solvent, the ratio of polymer to solvent/non-solvent, the temperatures of the first and the second drying zones and the speed of the moving web.

The porosity of the membrane produced can be
20 measured on a Gurley machine. This gives an indication of the relative porosity of different films measured using this machine. The machine measures the time taken in seconds for 100 cm^3 of air to pass through one square inch (6.45 cm^2) of the membrane at a small standard
25 pressure difference (1.215 kPa). This results in a reading known as a Gurley number or Gurley value. This can also be expressed as having the units Gurley seconds. Commercial films are available which give Gurley numbers (Gurley seconds) of from 400 to 600. Films with a Gurley
30 number of <60 tend to exhibit shorting when used in a battery. However, they may be suitable for use in fuel cells. The films with a Gurley number of from 50 to 200, more preferably 60 to 100, are preferred in the context of the present invention. As Gurley numbers increase the
35 porosity of the membrane decreases indicating that it is

harder to pass air through the membrane. This could be
due to the membrane having smaller pores or fewer larger
pores depending on the distribution of the pores.

5   Films as a thin as 5 μm can be made according to the
present invention. Thus, the films have a thickness of
at least 5 μm, preferably 10 to 30 μm, more preferably 15
to 25 μm, most preferably 17 to 22 μm.

10   One advantage of the present invention is that thin
films can be made which have adequate strength to be used
in a battery. The thin films also do not suffer from
shorting.

15   In a second aspect the present invention provides a
membrane comprising a polymer comprising vinylidene
fluoride with a thickness of from 5 to 30 μm and a Gurley
number of from 5 to 300 (Gurley seconds). The membranes
preferably have a Gurley number of from 50 to 200, more
20 preferably from 60 to 100, most preferably from 70 to 90.
Such membranes have not hitherto been available.

The present invention also provides the use of a
membrane of the present invention or of a membrane
25 produced according to the present invention as a
separator in a battery. The membrane is suitable for use
in a range of different types of battery, for example,
nickel-cadmium, nickel metal hydride, lithium ion and
lithium polymer batteries. The controllable porosity and
30 thickness of the membrane as well as the high strength of
these membranes makes them particularly advantageous for
this use.

The present invention also provides the use of a
35 membrane of the present invention or a membrane produced
according to the process of the present invention in a

- 10 -

fuel cell. The present invention also provides a laminate comprising a membrane of the present invention and the use of such a laminate in a fuel cell.

5   The present invention is now described in greater detail by way of example.

Examples

10   The Gurley numbers given for the membranes described in these examples were obtained on an Automatic Densometer model 4340 produced by Gurley Instruments of 514 Fulton Street, Troy, New York, USA.

15   Example 1

100 g PVdF (Solef 6020) having an intrinsic viscosity of 0.210 l/g (DMF, 25°C) was dispersed in 70 g of octanol. The slurry was stirred and 900 g of DMF was
20 added. The mixture was stirred for 1 day at 55°C and maintained at 55°C for 6 further days until complete solvation was achieved.

The solution was cast onto a polyester web moving at
25 0.5 m/minute using a knife-over-roll coating system. The blade gap was set to 0.32 mm and the drying zone temperatures were 65°C for zone 1 and 100°C for zone 2. This resulted in a finished microporous film with a thickness of 17 μm and an air permeability of 32 Gurley
30 seconds.

Increasing the drying temperatures to 80°C for zone 1 and 105°C for zone 2 produced a film with a thickness of 17 μm and an air permeability of 85 Gurley seconds.
35
Further increasing the drying temperatures to 95°C

- 11 -

for zone 1 and 110°C for zone 2 produced a film with a
thickness of 17 μm and an air permeability of 93 Gurley
seconds.

5   Example 2

100 g of PVdF (Solef 6020) having an intrinsic
viscosity of 0.210 1/g (DMF, 25°C) was dispersed in 80 g
of decanol. The slurry was stirred and 900 g of NMP was
10   added. The mixture was stirred and heated until complete
solvation was achieved as described in Example 1.
        The solution was cast onto a polyester web moving at
0.5 m/minute using a knife-over-roll coating system. The
blade gap was set to 0.32 mm. The drying zone
15   temperatures and film properties are set out in Table 1
below.

Table 1

	Example 2.1	Example 2.2
Drying zone temp. Zone 1 (°C)	95	110
Drying zone temp Zone 2 (°C)	110	130
Film thickness (μm)	14	16
Air permeability (Gurley secs)	12	40

20

        Example 3

100 g of PVdF (Solef 6020) having an intrinsic
25   viscosity of 0.210 1/g (DMF, 25°C) was dispersed in 70 g
of a 1:1 mixture (by weight) of decanol and dodecanol.
The slurry was stirred and 900 g of NMP was added. The
mixture was stirred for 1 day at 55°C and maintained at

- 12 -

55°C for 10 further days until complete solvation was achieved.

The solution was cast onto a polyester web moving at 0.5 m/minute using a knife-over-roll coating system. The blade gap was set to 0.32 mm. The drying zone temperatures and film properties are set out in Table 2 below.

Table 2

	Example 3.1	Example 3.2
Drying zone temp. Zone 1 (°C)	75	110
Drying zone temp. Zone 2 (°C)	110	130
Film Thickness (μm)	13	18
Air Permeability (Gurley secs)	70	180

Example 4

100 g of PVdF (Solef 6020) having an intrinsic viscosity of 0.210 1/g (DMF, 25°C) was dispersed in 100 g of a 1:1 mixture (by weight) of decanol and dodecanol. The slurry was stirred and 900 g of NMP was added. The mixture was stirred and heated until complete solvation was achieved as described in Example 3.

The solution was cast onto a polyester web moving at 0.5 m/minute using a knife-over-roll coating system. The blade gap was set to 0.32 mm. The drying zone temperatures and film properties are set out in Table 3 below.

- .13 -

Table 3

	Example 4.1	Example 4.2
Drying zone temp. Zone 1 (°C)	75	110
Drying zone temp. Zone 2 (°C)	110	130
Film Thickness (µm)	22	24
Air Permeability (Gurley secs)	9	55

It will be appreciated from the above Examples that the porosity becomes less (i.e. the Gurley number increases) if the dryer is at a higher temperature, and if the proportion of non-solvent is less. Film quality is generally improved if the difference in boiling point between the non-solvent and the solvent is greater than 25°C.

Example 5

100 g of PVdF (Solef 6020) having an intrinsic viscosity of 0.210 1/g (DMF, 25°C) was dispersed in 100 g of dodecanol. The slurry was stirred and 900 g of NMP was added. The mixture was stirred and heated until complete solvation was achieved as described in Example 1.

The solution was cast onto a polyester web moving at 0.5 m/minute using a knife-over-roll coating system. The blade gap was set to 0.30 mm. The drying zone temperatures and film properties are set out in Table 4 below.

- 14 -

Table 4

	Example 5
Drying zone temp. Zone 1 (°C)	75
Drying zone temp Zone 2 (°C)	110
Film thickness (μm)	24
Air permeability (Gurley secs)	76

5   Example 6

100 g of PVdF (Solef 6020) having an intrinsic viscosity of 0.210 l/g (DMF, 25°C) was dispersed in 80 g of dodecanol. The slurry was stirred and 900 g of NMP was
10 added. The mixture was stirred and heated until complete solvation was achieved as described in Example 1.

The solution was cast onto a polyester web moving at 0.5 m/minute using a knife-over-roll coating system. The blade gap was set to 0.32 mm. The drying zone
15 temperatures and film properties are set out in Table 5 below.

Table 5

	Example 6
Drying zone temp. Zone 1 (°C)	85
Drying zone temp Zone 2 (°C)	110
Film thickness (μm)	22
Air permeability (Gurley secs)	146

20

- 15 -

Example 7

100 g of PVdF (Solef 6020) having an intrinsic
viscosity of 0.210 1/g (DMF, 25°C) was dispersed in 60 g
5   of dodecanol. The slurry was stirred and 900 g of NMP was
added. The mixture was stirred and heated until complete
solvation was achieved as described in Example 1.

The solution was cast onto a polyester web moving at
0.5 m/minute using a knife-over-roll coating system. The
10 blade gap was set to 0.30 mm. The drying zone
temperatures and film properties are set out in Table 6
below.

Table 6

15

	Example 7
Drying zone temp. Zone 1 (°C)	85
Drying zone temp Zone 2 (°C)	110
Film thickness (µm)	19
Air permeability (Gurley secs)	88